

TABLE OF SHEAR ZONE TRENCH RESULTS

Sample Numbers	From (meters)	To (meters)	Channel Interval (meters)	Au assay (grams per tonne)	Au assay (grams per tonne)
				Company	QP Check
Shear Zone Trench					
T 001	0.0	1.2	1.2	0.00	
T 002	1.2	2.4	1.2	0.07	
T 003	2.4	3.7	1.2	0.10	
T 004	3.7	4.9	1.2	0.07	
T 005	4.9	6.1	1.2	0.17	
T 006	6.1	7.3	1.2	0.17	
T 007	7.3	8.5	1.2	2.84	
T 008	8.5	9.8	1.2	6.33	
T 009	9.8	11.0	1.2	10.17	
T 010	11.0	12.2	1.2	0.50	
T 011	12.2	13.4	1.2	20.47	
T 012	13.4	14.6	1.2	7.53	
T 013	14.6	15.9	1.2	5.33	
T 014	15.9	17.1	1.2	20.00	
T 015	17.1	18.3	1.2	16.97	
T 016	18.3	19.5	1.2	17.37	15.42
T 017	19.5	20.7	1.2	62.77	29.37
T 018	20.7	22.0	1.2	23.22	22.66
T 019	22.0	23.2	1.2	34.77	24.90
T 020	23.2	24.4	1.2	21.83	59.48
T 021	24.4	25.6	1.2	18.67	34.36
T 022	25.6	26.8	1.2	21.07	13.48
T 023	26.8	28.0	1.2	10.53	
T 024	28.0	29.3	1.2	32.42	
T 025	29.3	30.5	1.2	23.17	
T 026	30.5	31.7	1.2	39.15	
T 027	31.7	32.9	1.2	34.74	
T 028	32.9	34.1	1.2	25.95	
T 029	34.1	35.4	1.2	25.87	
T 030	35.4	36.6	1.2	1.57	
T 031	36.6	37.8	1.2	5.03	
T 032	37.8	39.0	1.2	19.87	
T 033	39.0	40.2	1.2	8.37	
T 034	40.2	41.5	1.2	23.00	
T 035	41.5	42.7	1.2	22.07	
T 036	42.7	43.9	1.2	40.23	
T 037	43.9	45.1	1.2	30.22	
T 038	45.1	46.3	1.2	27.00	
T 039	46.3	47.6	1.2	34.00	
T 040	47.6	48.8	1.2	19.33	
T 041	48.8	50.0	1.2	46.99	
T 042	50.0	51.2	1.2	22.77	
T 043	51.2	52.4	1.2	2.83	
T 044	52.4	53.7	1.2	1.43	
T 045	53.7	54.9	1.2	0.70	
T 046	54.9	56.1	1.2	0.57	
T 047	56.1	57.3	1.2	0.72	
T 048	57.3	58.5	1.2	0.40	
T 049	58.5	59.8	1.2	0.53	
T 050	59.8	61.0	1.2	0.60	
T 051	61.0	62.2	1.2	0.37	
T 052	62.2	63.4	1.2	0.40	
T 053	63.4	64.6	1.2	0.70	
T 054	64.6	65.9	1.2	1.27	
T 055	north end	vertical	2	0.57	
Main Mineralized Zone	7.3	53.7	46.4	20.69	
Trench Total	0.0	65.9	65.9	14.69	